



MOHM CHEMICAL SDN. BHD. (Co. No. 276851-U)

MCX MARKETING SDN. BHD. (Co. No. 363532-T)

H. Q. : No. 32, Jalan Temenggong, Off Jalan Tampoi, 81100 Johor Bahru, Johor, Malaysia.

Tel : (60 7) 333 1222 Fax : (60 7) 332 0545 / 333 7919

KL. Office : No. 4, Jalan TPP 5/10, Taman Perindustrian Puchong, 47100 Puchong, Selangor.

Tel : (60 3) 8060 0370 / 8060 0372 Fax : (60 3) 8060 0723

Email : info@mochem.com Website: www.mochem.com / www.xtraseal.com

TECHNICAL DATA SHEET

x'traseal® 625°F XTRA GRAY RTV SILICONE

DESCRIPTION:

x'traseal® 625°F XTRA GRAY 100% RTV SILICONE IS A ONE PART SILICONE SEALANT THAT CURE TO FORM A DURABLE RUBBER SEAL THAT OFFER EXCELLENT ADHESION, HEAT RESISTANT FOR GLAZING AND JOINT SEALING APPLICATION.

FEATURES:

- ◆ LOW ODOR NEUTRAL CURING SYSTEM.
- ◆ NON-CORROSIVE TO METALS.
- ◆ NON-CORROSIVE TO AUTOMOBILES.
- ◆ OUTSTANDING HIGH TEMPERATURE RESISTANT UPTILL 330°C.
- ◆ EXCELLENT GUNNABILITY (-20°C TO 50°C).
- ◆ PRIMERLESS ADHESION TO MOST MATERIALS.

USES:

HIGH TEMPERATURE RESISTANT GASKET AND JOINT SEALING.
ASSEMBLIES OF GLASS, PORCELAIN COATED METAL, EPOXY AND POLYESTER PANELS,
POLYSTYRENE, ANODISED ALUMINIUM AND FINISHED WOOD.

LIMITATIONS:

GREY 100% RTV SILICONE IS NOT PAINTABLE.
NOT FOR: PE, PP, PTFE AND BITUMINOUS SURFACE.

JOINT DESIGN:

THE SPECIFIED SEALANT BEAD SIZE SHOULD BE CALCULATED TO COMPLY WITH THE COMPRESSION AND EXTENSION CAPABILITIES OF THE SEALANT IN RELATION TO THE ANTICIPATED JOINT WIDTH DUE TO THERMAL EXPANSION AND CONTRACTION.

GENERALLY CALCULATION OF THE WIDTH OF SEALANT BEAD SHOULD BE COMPUTED ON THE BASIS OF A MAXIMUM $\pm 25\%$ COMPRESSION AND EXTENSION CAPABILITY MINIMUM BEAD SIZE SHOULD NOT BE LESS THAN 3mm TO ACCOMMODATE MOVEMENT. DESIGN JOINT DEPTH OF WHICH RATIO WIDTH BECOMES 0.5 TO 1.

SUITABLE JOINT DEPTH VS. WIDTH:

6mm x 6mm
8mm x 12mm
10mm x 20mm

- * JOINT SIZE MINIMUM 3mm x 3mm.
- * JOINT SIZE MAXIMUN 30mm.



MOHM CHEMICAL SDN. BHD. (Co. No. 276851-U)
MCX MARKETING SDN. BHD. (Co. No. 363532-T)
H. Q. : No. 32, Jalan Temenggong, Off Jalan Tampoi, 81100 Johor Bahru, Johor. Malaysia.
Tel : (60 7) 333 1222 Fax : (60 7) 332 0545 / 333 7919
KL. Office : No. 4, Jalan TPP 5/10, Taman Perindustrian Puchong, 47100 Puchong, Selangor.
Tel : (60 3) 8060 0370 / 8060 0372 Fax : (60 3) 8060 0723
Email : info@mochem.com Website: www.mochem.com / www.xtraseal.com

TECHNICAL DATA SHEET

x'traseal[®] 625°F XTRA GRAY RTV SILICONE

APPLICATION:

- ◆ SURFACE MUST BE CLEAN AND DRY.
- ◆ MASK SMOOTH SURFACE TO SIMPLIFY CLEAN UP.
- ◆ CUT NOZZLE TO DESIRED SIZE.
- ◆ PUSH SEALANT AHEAD FOR UNIFORM BEAD.
- ◆ TOOL WITHIN 5 MINUTES.
- ◆ CLEAN OFF EXCESS SEALANT WITH M.E.K. OR TOLUENE.

CURING TIME:

XTRA GRAY 100% RTV SILICONE WILL TACK FREE IN APPROXIMATELY 15 MINUTES AND WILL CURE TO A DEPTH OF 10mm WITHIN 7 DAYS.

SPECIFICATION:

CURING SYSTEM	NEUTRAL (OXIME)
APPEARANCE	NON-SAGGING PASTE
ODOUR	OXIME SMELL
SPECIFIC GRAVITY	1.04±0.01
SHORE A HARDNESS	APPROX. 30.
ELONGATION	400%
TENSILE STRENGTH	APPROX. 1.2MPa.
TACK FREE TIME	15 MINUTES
APPLICATION TEMP.	-20°C TO 50°C
SERVICE TEMPERATURE	-40°C TO 330°C.
SHELF LIFE	12 MONTHS

CAUTION:

UNCURED SEALANT MAY CAUSE SKIN, EYE AND RESPIRATORY SYSTEM IRRITATION.
USE ONLY IN WELL VENTILATED AREAS.
USE APPROPRIATE PERSONAL PROTECTION TO AVOID CONTACT WITH SKIN AND EYES.
IN CASE OF EYE CONTACT OR IRRITATION, FLUSH EYE IMMEDIATELY WITH RUNNING WATER FOR 15 MINUTES AND GET MEDICAL ATTENTION.
IN CASE OF SKIN CONTACT, WASH AFFECTED AREAS WITH HAND CLEANER FOLLOWED BY SOAP AND WATER.
PRODUCT RELEASES KETOXIME DURING APPLICATION AND CURING.
FOR FURTHER HEALTH AND SAFETY INFORMATION CONSULT THE CURRENT MATERIAL SAFETY DATA SHEET.