



**MOHM CHEMICAL SDN. BHD.** (Co. No. 276851-U)  
**MCX MARKETING SDN. BHD.** (Co. No. 363532-T)  
H. Q. : No. 32, Jalan Temenggong, Off Jalan Tampoi, 81100 Johor Bahru, Johor, Malaysia.  
Tel : (60 7) 333 1222 Fax : (60 7) 332 0545 / 333 7919  
KL. Office : No. 4, Jalan TPP 5/10, Taman Perindustrian Puchong, 47100 Puchong, Selangor.  
Tel : (60 3) 8060 0370 / 8060 0372 Fax : (60 3) 8060 0723  
Email : info@mochem.com Website: www.mochem.com / www.xtraseal.com

## TECHNICAL DATA SHEET

### **x'traseal®** AWNING CAULK JOINT SEALING & WATERPROOFING COMPOUND

#### **DESCRIPTION:**

**x'traseal®** AWNING CAULK IS ONE PART SEALANT THAT OFFER EXCELLENT ADHESION, OUTSTANDING DURABILITY AND EXCELLENT GUNNABILITY FOR GENERAL SEALING APPLICATION.

#### **FEATURES:**

- ◆ OUTSTANDING DURABILITY
- ◆ ONE PART NO MIXING
- ◆ FLEXIBLE ( $\pm 3\%$ )
- ◆ EXCELLENT GUNNABILITY ( $-20^{\circ}\text{C}$  TO  $50^{\circ}\text{C}$ )
- ◆ WEATHER PROOF
- ◆ LOW SHRINKAGE
- ◆ NO SAGGING
- ◆ PRIMERLESS ADHESION TO MOST MATERIALS

#### **USES:**

GENERAL JOINT SEALING IN EXTERNAL WALLING, WINDOW AND DOOR FRAMES, ROOFS AND OTHERS.

#### **LIMITATIONS:**

AWNING CAULK IS NOT SUITABLE FOR HIGH JOINT MOVEMENT SUBSTRATE (MORE THAN  $\pm 3\%$  JOINT MOVEMENT).

#### **CURING TIME:**

AWNING CAULK WILL TACK FREE IN APPROXIMATELY 24 HOURS.

#### **APPLICATION:**

- ◆ SURFACE MUST BE CLEAN AND DRY.
- ◆ MASK SMOOTH SURFACE TO SIMPLIFY CLEAN UP.
- ◆ USE APPROVED BACK-UP MATERIAL IN JOINT.
- ◆ CUT NOZZLE TO DESIRED SIZE.
- ◆ INSERT CARTRIDGE INTO CAULKING GUN.
- ◆ PUSH SEALANT AHEAD FOR UNIFORM BEAD.
- ◆ TOOL WITHIN 10 MINUTES.
- ◆ CLEAN OFF EXCESS SEALANT WITH MINERAL SPIRIT.



**MOHM CHEMICAL SDN. BHD.** (Co. No. 276851-U)  
**MCX MARKETING SDN. BHD.** (Co. No. 363532-T)  
H. Q. : No. 32, Jalan Temenggong, Off Jalan Tampoi, 81100 Johor Bahru, Johor, Malaysia.  
Tel : (60 7) 333 1222 Fax : (60 7) 332 0545 / 333 7919  
KL.Office : No. 4, Jalan TPP 5/10, Taman Perindustrian Puchong, 47100 Puchong, Selangor.  
Tel : (60 3) 8060 0370 / 8060 0372 Fax : (60 3) 8060 0723  
Email : info@mochem.com Website: www.mochem.com / www.xtraseal.com

## TECHNICAL DATA SHEET

### **x'traseal®** AWNING CAULK JOINT SEALING & WATERPROOFING COMPOUND

#### **SPECIFICATION:**

CURING SYSTEM	OXIDIZING
APPEARANCE	NON-SAGGING PASTE
ODOUR	OLEO-RESINOUS
SPECIFIC GRAVITY	1.60±0.3
MAX. JOINT MOVEMENT	±3%
SHRINKAGE	5 %
TACK FREE TIME	24 HOURS
APPLICATION TEMP.	4°C TO 50°C
SERVICE TEMP.	-5°C TO 60°C
SHELF LIFE	12 MONTHS

#### **CAUTION:**

UNCURED SEALANT MAY CAUSE SKIN, EYE AND RESPIRATORY SYSTEM IRRITATION.  
USE APPROPRIATE PERSONAL PROTECTION TO AVOID CONTACT WITH SKIN AND EYES.  
IN CASE OF EYE CONTACT OR IRRITATION, FLUSH EYE IMMEDIATELY WITH RUNNING WATER FOR 15 MINUTES AND GET MEDICAL ATTENTION.  
IN CASE OF SKIN CONTACT, WASH AFFECTED AREAS WITH HAND CLEANER FOLLOWED BY SOAP AND WATER.  
FOR FURTHER HEALTH AND SAFETY INFORMATION CONSULT THE CURRENT MATERIAL SAFETY DATA SHEET.