



**MOHM CHEMICAL SDN. BHD.** (Co.No.276851-U)  
**MCX MARKETING SDN. BHD.** (Co.No.363532-T)

H. Q. : No.32, Jalan Temenggong, Off Jalan Tampoi, 81100 Johor Bahru, Johor. Malaysia.  
Tel : (60 7) 333 1222 Fax : (60 7) 332 0545 / 333 7919  
Branch : No.43, Jalan Tambur 33/19, Sek.33, Shah Alam Technology Park,  
47100 Shah Alam, Selangor. Malaysia.  
Tel: (60 3) 5124 0876 / 5124 0878 Fax: (60 3) 5124 0877  
Email: info@mochem.com Website: www.mochem.com / www.xtraseal.com

## TECHNICAL DATA SHEET

### xtraseal® LIQUID GASKET

#### DESCRIPTION:

**xtraseal®** LIQUID GASKET IS A SEMI-DRYING GRAY LIQUID GASKET THAT USES RUBBER AS THE MAIN INGREDIENTS. IT IS FORMULATED TO FORM A LAYER THICK ENOUGH TO WORK EFFICIENTLY ON UNEVEN JOINT SURFACES. IT HAS A DISTINGUISHING ABILITY TO TURN INTO RUBBER-LIKE ELASTIC SUBSTANCES WITH EXCELLENT RESISTANCE TO HEAT, OIL, GASOLINE AND PARTICULARLY LPG. IDEAL FOR THE PURPOSE OF MAKING QUALITY GASKETS IN GARAGES, WORKSHOPS, HOMES AND DO-IT-YOURSELF.

#### FEATURES:

- ◆ A VISCO-ELASTIC TYPE SEALANT CAPABLE OF JOINING UNEVEN SURFACES.
- ◆ EXCELLENT RESISTANCE TO HEAT, OIL, GASOLINE AND LPG.
- ◆ EASY TO APPLY AND ALLOW TO AUTOMATE THE PRODUCTION LINE WITH LABOR- SAVING EQUIPMENTS, MARKEDLY IMPROVING THE WORK EFFICIENTLY.
- ◆ HAS THE PROPERTY OF FLOWING AT ROOM TEMPERATURE.

#### APPLICATION:

- ◆ SURFACES MUST BE CLEAN, DRY, AND FREE FROM MOISTURE, GREASE AND OTHER STAINS BEFORE APPLICATION.
- ◆ APPLY A THIN AND UNIFORM LAYER OF LIQUID GASKET ON BOTH MATING SURFACES.
- ◆ ASSEMBLE ABOUT 1 MINUTE AFTER APPLICATION.
- ◆ APPLICATION TEMPERATURE RANGE IS FROM -40°C TO +150°C.
- ◆ SEAL TIGHTLY AFTER USE. STORE IN A COOL DRY PLACE.

#### SPECIFICATION:

APPEARANCE	GRAY HIGH VISCOSITY LIQUID
SOLID CONTENT	46 ± 1%
VISCOSITY AT 30°C	9000 - 12000CPS
MAIN SOLVENT	HYDROCARBON SOLVENT
MAIN INGREDIENT	CHLOROPRENE RUBBER
DILUTION	TOLUENE
TEMPERATURE RANGE	40°C TO 150°C

#### CAUTION:

AVOID BREATHING IN VAPOR. UNCURED SEALANT MAY CAUSE IRRITATION. USE APPROPRIATE PERSONAL PROTECTION TO AVOID CONTACT WITH SKIN AND EYES. IN CASE OF EYE CONTACT OR IRRITATION, FLUSH EYE IMMEDIATELY WITH RUNNING WATER FOR 15 MINUTES AND GET MEDICAL ATTENTION. IN CASE OF SKIN CONTACT, WASH AFFECTED AREAS WITH HAND CLEANER FOLLOWED BY SOAP AND WATER. USE WITH ADEQUATE VENTILATION. HIGHLY INFLAMMABLE PRODUCT. FOR FURTHER HEALTH AND SAFETY INFORMATION CONSULT THE CURRENT MATERIAL SAFETY DATA SHEET.